



江苏苏青水处理工程集团有限公司

Jiangsu Suqing Water Treatment Engineering Group Co., Ltd.

苏青半导体水处理前置混床阴阳离子交换树脂

Suqing Pretreatment Mixed-Bed Ion Exchange Resin for Semiconductor

在半导体超纯水（UPW）制备系统中，前置混床是指位于反渗透（RO）之后、电去离子（EDI）之前的关键去离子单元。其内部装填的阴阳离子交换树脂承担着主脱盐和保护下游精密设备的双重核心任务。苏青前置混床由强酸阳离子和强碱阴离子树脂的混合，具有良好的化学稳定性、高交换容量和优异的动力学性能，以满足半导体水处理系统连续、稳定、高效运行的需求。

In a semiconductor Ultrapure Water (UPW) production system, the "pretreatment mixed bed" is a critical deionization unit positioned after Reverse Osmosis (RO) and before Electrodeionization (EDI). The cation and anion exchange resins loaded within it serve the dual core functions of primary demineralization and protecting downstream sensitive equipment. Suqing Pretreatment mixed-bed is mixture of strong acid cation and strong anion exchange resins. They possess good chemical stability, high exchange capacity, and excellent kinetic performance to meet the demands of continuous, stable, and efficient operation in semiconductor water treatment systems.

▲ 树脂的物化性能指标(Physical and Chemical Properties)

项目		混床树脂 Pretreatment Mixed-Bed	
混床树脂组成		SQ-680EG MB	SQ-740EG MB
总交换容量(Total Capacity)	mmol/ml≥	2.0	1.2
含水量(Water Retention)	%	43-48	50-60
湿视密度(Density)	g/ml	0.78-0.85	0.66-0.71
湿真密度(Bulk Density)	g/ml	1.25-1.30	1.06-1.10
粒度范围(Particle Size)	%	(0.55-0.75mm)≥95	(0.5-0.7mm)≥95
有效粒径(Effective Size)	mm	0.6-0.7	0.55-0.65
均一系数(Uniformity Coefficient)	≤	1.2	1.2
转型膨胀率(Swelling, Na→H)	%≤	10	25
磨后圆球率(Whole Beads after Attrition) %≥		95	95
出厂型态(Shipping Ion Form)		Na	Cl

▲ 包装(Packing)

50 升/桶装 (50L/Drum)

江苏苏青水处理工程集团有限公司

Jiangsu Suqing Water Treatment Engineering Group Co., Ltd.

地址(Add): 江苏省江阴市河塘长青路 89 号

No.89 Changqing Road, Hetang, Jiangyin, Jiangsu, China

电话(Tel): 0510-86331801

传真(Fax): 0510-86331113

E-mail: suqingsxj@suqing.com

<http://www.suqing.com>

www.suqing.com





江苏苏青水处理工程集团有限公司

Jiangsu Suqing Water Treatment Engineering Group Co., Ltd.

苏青半导体水处理抛光树脂 SQ-8050UP

Suqing Semiconductor Grade Water Treatment Polishing Resin SQ-8050UP

苏青 SQ-8050UP 是一种半导体级高纯超纯水用离子交换树脂，由再生均匀的阳离子交换树脂和阴离子交换树脂以等比混合而成。不仅可以管理采出水的纯度，而且可以管理总有机碳（TOC）。主要用于生产高纯度超纯水，应用于 LCD、OLED 和 半导体。

Suqing SQ-8050UP is an ion exchange resin for semiconductor grade high-purity ultrapure water, which is produced by mixing regenerated uniform cation and anion exchange resins in equal capacity ratio. It is possible to manage not only the purity of the produced water but also the Total Organic Carbon (TOC). Mainly used to produce high-purity ultrapure water in fields such as LCD, OLED and semiconductors.

▲ 树脂的物化性能指标(Physical and Chemical Properties)

项目	SQ-8050UP	
	阳树脂 Cation	阴树脂 Anion
树脂骨架(Matrix Structure)	Styrene-DVB,Gel	Styrene-DVB,Gel
总交换容量(Total Capacity) mmol/ml≥	1.9	1.0
出厂型态(Shipping Ion Form)	H ⁺	OH ⁻
粒度范围(Particle Size) mm	0.62±0.05	0.62±0.05
均一系数(Uniformity Coefficient)	1.10↓	1.10↓
离子转型率(Ionic Conversion) %	H ⁺ 99.0↑	OH ⁻ 95.0↑ Cl ⁻ 1.0↓
进水要求(Inlet condition)	超纯水, 电阻率>17.5 MΩ·cm, TOC<2ppb,SV30 Ultrapure water, Resistivity>17.5 MΩ·cm, TOC<2ppb, SV30	
出水水质(Outlet condition)	保证电阻率>18.2·cm↑(30 分钟) △TOC<1ppb (180 分钟) Guaranteed Resistivity>18.2 MΩ·cm↑(in 30min.) △TOC<1ppb(in 180min.)	

▲ 包装(Packing)

50 升/桶装 (50L/Drum)

江苏苏青水处理工程集团有限公司
Jiangsu Suqing Water Treatment Engineering Group Co.,Ltd.
地址(Add): 江苏省江阴市河塘长青路 89 号
No.89 Changqing Road,Hetang,Jiangyin,Jiangsu,China
电话(Tel): 0510-86331801
传真(Fax): 0510-86331113
E-mail: suqingsxj@suqing.com
<http://www.suqing.com>

